

MORSUN ANTIFOULING COATING (IS-1419)

PRODUCT CODE

MCS-AF-613

PRODUCT DESCRIPTION

A Conventional Marine Antifouling Paint with high content of Cuprous Oxide and Organic biocides. This antifouling Coating after application of second coat should preferably be immersed within 24 hours

SUGGESTED USES

As an Antifouling Coating from keel to light load line

TECHNICAL DATA

Colour	Red
Finish	Semi Glossy
Flash Point	> 30°C
Volume Solids	50% ± 2
Recommended DFT	40μ per coat
Covering Capacity	12.5 M ² /ltr. On a smooth and non-absorbent surface at a recommended dft of 40μ
With 30% Loss	8.8 M ² /ltr
Drying Time	Surface Dry : 1 hour maximum
Hard Dry	Overnight
Mode of Application	Brush/Roller/Con./Airless Spray
Airless Spray	Tip Size : 0.017" – 0.021"
Fluid Pressure	2500 – 3000 psi
Thinner Recommended	Morsun G.P. Thinner
Overcoating Intervals	Minimum 5 Hours. Maximum 18-24 Hours
Surface Preparation	The base coat, Anti-corrosive Chocolate should be dry and free from all surface contaminants and should be coated within the specified time
Shelf Life	6 Months
Packing	4 Litres, 20 Litres

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.