

MORSUN SYNTHETIC ALUMINIUM PAINT

PRODUCT CODE**MCS-AL-023****PRODUCT DESCRIPTION**

A superior quality single pack Aluminium paint. Recommended for use in cargo holds, engine casing (where the temp. does not exceed 90-100°C) guard rails etc

TECHNICAL DATA

Colour	Aluminium
Finish	Lustrous Aluminium
Flash Point	> 30° C
Volume Solids	45% ±2
Recommended DFT	50 – 60μ
Theoretical Covering	14M ² per ltr. at 30μ
With 30% Loss	9.8 M ² per ltr
Mode of Application	Brush / Roller /Airless/Con. Spray
Airless Spray	Tip size : 0.015-0.021
Fluid Pressure	2000-2500 psi
Thinner Recommended	Morsun G. P. Thinner
Drying Time	Surface Dry : 1 hour maximum
Hard Dry	Overnight
Overcoating Interval	24 hours Minimum, No Maximum
Subject to Use	48 hours minimum
Surface Preparation	Surface should be free from all contaminants dry and suitably primed
Shelf Life	12 months
Packing	20 litres, 4 litres

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.