

MORSUN SYNTHETIC UNDER COAT

PRODUCT CODE**MCS-AL-025****PRODUCT DESCRIPTION**

A high quality synthetic Resin based Marine undercoating

SUGGESTED USES

Ideal for use as an undercoat to Top Coat Enamels. Quick drying coating with good application characteristics

TECHNICAL DATA

Colour	White / D.A. Grey
Finish	Matt
Flash Point	> 30°C
Volume Solids	50% ±2
Recommended DFT	30 to 40μ
Theoretical Covering	12.5 M ² per ltr. at 40μ
With 30% Loss	8.75 M ² per ltr
Mode of Application	Brush / Roller / Airless /Con. Spray
Airless Spray	Tip Size: 0.018"-0.024"
Fluid Pressure	2000-3000 psi
Thinner	Morsun G. P. Thinner
Drying Time	Surface Dry : 1hour maximum
Hard Dry	Overnight
Overcoating Interval	24 hours, No Maximum
Surface Preparation	Surface should be clean, dry and free from all contaminants and suitably primed
Shelf Life	12 months
Packing	20 litres, 4 litres
Precautions	Ventilate the area to be painted thoroughly to avoid suffocation while application

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.