

## MORSUN SYNTHETIC TOPCOAT ENAMEL

**PRODUCT CODE****MCS-AL-026****PRODUCT DESCRIPTION**

A superior quality full gloss Enamel based on Synthetic Resin and weather resistant pigments

**SUGGESTED USES**

Recommended for use both as a protective and decorative coating for interior and exterior areas above water with good application properties and flow. It dries in a short time providing a smooth finish

**TECHNICAL DATA**

|                      |                                                                                    |
|----------------------|------------------------------------------------------------------------------------|
| Colour               | As required                                                                        |
| Finish               | Glossy                                                                             |
| Viscosity            | 80 – 120 Seconds                                                                   |
| Flash Point          | > 30° C                                                                            |
| Volume Solids        | 40 ±2 %                                                                            |
| Recommended DFT      | 25-30 µm                                                                           |
| Theoretical Covering | 16.0 M <sup>2</sup> per ltr. at 25µm                                               |
| With 30% Loss        | 11.20 M <sup>2</sup> per ltr                                                       |
| Mode of Application  | Brush / Roller /Airless/Con. Spray                                                 |
| Airless Spray        | Tip size : 0.015"-0.021"                                                           |
| Fluid Pressure       | 2000-2500 psi                                                                      |
| Thinner Recommended  | Morsun G. P. Thinner                                                               |
| Drying Time          | Surface Dry : 2 hour                                                               |
| Hard Dry             | Overnight                                                                          |
| Overcoating Interval | 24 hours Minimum, No Maximum                                                       |
| Surface Preparation  | Surface should be free from all contaminants dry and suitably primed               |
| Shelf Life           | 12 months                                                                          |
| Packing              | 20 litres, 4 litres                                                                |
| Precautions          | Ventilate the area to be painted thoroughly to avoid suffocation while application |

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.