

MORSUN SUPER SYNTHETIC ENAMEL

PRODUCT CODE**MCS-AL-029****PRODUCT DESCRIPTION**

A superior quality full gloss Enamel based on Synthetic Resin and weather resistant pigments

SUGGESTED USES

Recommended for use both as a protective and decorative coating for interior and exterior areas above water / ground with good application properties and flow. It dries in a short time providing a smooth finish

TECHNICAL DATA

Colour	As required
Finish	Glossy
Solid Volume	48% $\pm$ 2
Recommended DFT	50 μ
Theoretical Covering	9.6 M ² per ltr. at 50 μ
With 30% Loss	6.8 M ² per ltr
Mode of Application	Brush / Roller /Airless/Con. Spray
Airless Spray	Tip size : 0.015-0.021
Fluid Pressure	2000-2500 psi
Thinner Recommended	Morsun G. P. Thinner
Drying Time	Surface Dry : 1 hour
Hard Dry	O/N
Overcoating Interval	24 hours Minimum, No Maximum
Surface Preparation	Surface should be free from all contaminants dry and suitably primed
Shelf Life	12 months
Packing	20 litres, 4 litres

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.