

MORSUN SYNTHETIC ZINC PHOSPHATE PRIMER GREY (ZP)

PRODUCT CODE

MCS-AL-037

PRODUCT DESCRIPTION

A general purpose primer based on synthetic Resin medium with Zinc Phosphate anti-corrosive pigment. Recommended for use on Mild Steel Structures, above water area of ships like Boot top, topside, decks, superstructures, cargo holds, etc. This primer can be over coated with a wide range of Synthetic Enamel finishes. Product composition is free from Lead and Chromes

TECHNICAL DATA

Colour	Grey
Finish	Matt to Egg-shell
Flash Point	> 30° C
Volume Solids	44% ±2
Recommended DFT	40μ
Theoretical Covering	11 M ² per ltr. at 40μ
With 30% Loss	7.7 M ² per ltr
Mode of Application	Brush / Roller /Airless / Con. Spray
Airless Spray	Tip Size: 0.018"-0.024"
Fluid Pressure	2000-3000 psi
Thinner	Morsun G. P. Thinner
Drying Time	Surface Dry : 1 hour maximum
Hard Dry	Overnight
Overcoating Interval	Overnight, No Maximum
Surface Preparation	Degrease and blast clean to Sa 2 ½. If blast cleaning is not possible follow manual/mechanical means, e.g. Chipping scarping, wire-brushing, power tool cleaning etc. to remove all rust, scale, loose particles, contaminants, etc. Ensure removal of weld spatters, seams and sharp edges. Dry off and paint
Shelf Life	12 months
Packing	20 litres, 4 litres
Precautions	Ventilate the area to be painted thoroughly to avoid suffocation while application

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.