

MORSUN SYNTHETIC BITUMASTIC ALUMINIUM PRIMER

PRODUCT CODE

MCS-AL-039

PRODUCT DESCRIPTION

An excellent protective Primer for underwater steel based on specially formulated bituminous medium pigmented with aluminium flakes. It ensures high water resistance and provides good film strength thus protecting the steel from corrosion

SUGGESTED USES

As an Anti-corrosive primer for steel hull of ships for the bottom and boot-top area

TECHNICAL DATA

Colour	Grayish Black
Finish	Semi Glossy with Metallic Lusture
Flash Point	> 30°C
Volume Solids	50% ±2
Recommended DFT	40μ
Covering Capacity	12.5 M ² /ltr. at 40μ
With 30% Loss	8.7M ² per ltr
Method of Application	Brush/Roller/Con./Airless Spray
Airless Spray	Tip Size : 0.018" – 0.024"
Fluid Pressure	2500 – 3000 psi
Drying Time	Surface Dry : 20 – 30 mts
Hard Dry	8 – 10 hrs
Overcoating Interval	Minimum 8 – 10 Hours. Maximum None
Thinner Recommended	Morsun G. P. Thinner
Surface Preparation	Blast clean new steel surface to be painted to Sa 2½. For repair work the surface may be cleaned using mechanical tooling, chipping, wire brushing, etc. Ensure the surface is free from all contaminants like oil, grease, dust, rust, etc. prior to application of primer
Shelf Life	12 Months
Packing	4 Litres, 20 Litres

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.