

MORSUN SYNTHETIC RED LEAD PRIMER

PRODUCT CODE

MCS-AL-041

PRODUCT DESCRIPTION

A single pack quick drying Red Lead Primer (modified alkyd medium pigmented with Red Lead) suitable for over-coating with conventional finishes & chlorinated rubber based coatings

SUGGESTED USES

Recommended for use on bridges, cranes, towers, equipment, tanks, etc., on exterior hull of ships, below, above water line and superstructure and especially as a primer on structural steel subject to aggressive environment

TECHNICAL DATA

Colour	Orange
Finish	Semi-Glossy
Flash Point	> 30° C
Volume Solids	40% + 2
Recommended DFT	30 to 40μ per coat
Theoretical Covering Capacity	10 M ² @ 40μ per coat
At 30% loss	7M ²
Method of Application	Brush / Roller /Spray
Thinner Recommended	Morsun G.P. Thinner
Airless Spray	Tip Size: 0.021"- 0.026" : Fluid Pressure: 2500- 3000 Psi
Drying Time	Surface Dry : 1 - 2 Hours
Hard Dry	Overnight
Overcoating Interval	Overnight for conventional and 24 hours minimum for CR based paints
Surface Preparation	Degrease and blast clean to Sa 2 ½. If blast cleaning is not possible follow manual/mechanical means, e.g. Chipping scarping, wire-brushing, power tool cleaning etc. to remove all rust, scale, loose particles, contaminants, etc. Dry off and paint
Storage Life	9 months in Sealed Containers
Packing	20 Litres, 4 Litres

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.