

MORSUN SYNTHETIC HIGH PERFORMANCE MARINE PRIMER RED/GREY

PRODUCT CODE**MCS-AL-042****PRODUCT DESCRIPTION**

Primer based on Modified Acrylic Synthetic Resin medium with anticorrosive pigments (viz. Red Oxide, Zinc Chromate & Zinc Phosphate). Recommended for use on above water area of ships like Boot top, topside, decks, superstructures, cargo holds, etc. Primed surface can be over coated with Modified Acrylic Finish CR-122

TECHNICAL DATA

Colour	Red / Grey
Finish	Matt to Egg-shell
Flash Point	> 28° C
Volume Solids	42% ±2
Recommended DFT	40μ to 75μ
Theoretical Covering	10.50 M ² per ltr. at 40μ
With 30% Loss	7.35 M ² per ltr. at 40μ
Mode of Application	Brush / Roller /Airless
Airless Spray	Tip Size: 0.018"-0.024"
Fluid Pressure	1750-2600 psi
Thinner	Morsun G. P. Thinner
Drying Time	Surface Dry : 30 to 45 minutes
Hard Dry	8 Hours
Overcoating Interval	Minimum: 8 Hours, No Maximum
Surface Preparation	Degrease and blast clean to Sa 2 ½. If blast cleaning is not possible follow manual/mechanical means, e.g. Chipping scarping, wire-brushing, power tool cleaning etc. to remove all rust, scale, loose particles, contaminants, etc. Ensure removal of weld spatters, seams and sharp edges. Dry off and paint
Shelf Life	12 months
Packing	20 litres, 4 litres
Precautions	Ventilate the area to be painted thoroughly to avoid suffocation while application. (Note: Unless specified, all Technical Parameters are checked at 30 °C)

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.