

MORSUN SYNTHETIC ENAMEL INTERIOR UNDERCOATING PAINT (CONFIRMING TO IS-133)

PRODUCT CODE

MCS-AL-048

PRODUCT DESCRIPTION

It is a high quality synthetic based product having excellent adhesion and holding strength with finish coat, can be overcoated with enamel or emulsion paint

SUGGESTED USES

This is Interior undercoat product used for decorating and protection of interior surface and is normally applied as painting system as an appropriate primer followed by finish topcoat paint

TECHNICAL DATA

Colour	All Shades
Finish	Smooth Matt to Eggshell
Gloss	0-20 unit
Volume Solids	37 ± 2 %
Recommended dft	35-50 μ
Theoretical Covering	9.25 M2 at 40μ
Method of Application	Brush / Roller for small area, Conventional/ Airless spray for bigger areas
Heat Resistance	Upto 60°C dry heat (Intermittently)
Thinner Recommended	Sunthane Thinner
Airless Spray	Tip size: 0.015"- 0.019" : Fluid pressure: 2000- 2500 psi
Drying Time	Surface Dry : 2 hours
Tack Free	8 hours
Hard Dry	24 hours
Flash Point	30 deg C
Overcoating Interval	12 hours
Shelf Life	12 months in sealed container stored at room temperature
Packing	20 litres, 4 litres
Precautions	Avoid inhalation. Take necessary precautions to avoid contact with skin or eyes. Ventilate the area

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.