

MORSUN SYNTHETIC UNDERCOAT IS 2933 (U)

PRODUCT CODE
MCS-AL-052

PRODUCT DESCRIPTION

Morsun Synthetic Undercoat Paint is offered as an economical and durable finish paint. It is recommended mainly for interior and exterior use. Its superior flow and leveling properties are well known and make it best choice amongst the economically priced enamels so very excellent to Low Cost Paint and general purpose domestic and industrial Paint meet to specification of IS 2933

TECHNICAL DATA

USER GUIDE	Morsun Synthetic Undercoat Paint has very excellent Flexibility Adhesion to Steel & Metal Structure, Wooden and Plaster Surface & also very excellent Resistance to Water, Corrosion and Weather effects
SURFACE PREPARATION	The Surface to be painted should be free from Rust, Grease and Oil etc. and should be dry and free from loose matter. Degreasing and de-rusting can be done by suitable treatment. In case of new or bare surface, it should be applied over an appropriate primer. Then one coat of Morsun Undercoat is to be applied after drying for 10-12 hours. Apply Morsun Synthetic Undercoat using recommended thinner, For best result, it is advisable to apply two coats of Morsun Synthetic Enamel giving 10-12 hours of drying between the coats
Colour	Selected Range / As IS Shade Card
Finish	Smooth & Matt to Eggshell
Viscosity	80 – 120 Secs. By Ford cup B-4
Gloss	At 60° head 0-5
Flash Point	Above 30 Deg. C
True Pigments	48% + 2
Binder Solid	19% + 2
Volume Solids	43% to 45%
Recommended DFT	30 microns / Coat
Covering Capacity (Brushing)	12-16 sqm./ltr/Coat at 30 microns DFT Drying Time at 30°C - 35°C : Surface Dry: 8 Hours Maximum
Hard Dry	18 Hours Maximum
Tack Free	24 Hours Maximum
Application Method	Brushing Spraying – at a Pressure of 2.75-35/Cm ² (40-50 PSI)
Recommended Primer	Metal- Red Oxide-2074 or Primer Surfacer on Surface Grey-White Wood- Primer Pink or White (Synthetic) Cement – Water Base Cement Primer
Recommended Application	A – Brushing 55-60 Sec. by B-4 Cup at 30° C B – Spraying 25-30 Sec. by B-4 Cup at 30° C
Thinner Recommended	Morsun G. P. Thinner

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.