

MORSUN SUNCHLOR FINISH

PRODUCT CODE
MCS-CR-121
PRODUCT DESCRIPTION

A single pack chlorinated rubber based finish paint plasticised with chlororubber medium suitably pigmented

SUGGESTED USES

The product is ideal for use on boot-top, topside, decks, superstructures, freight containers and certain other interior locations. When dried the coating provides a film resistant to marine conditions

TECHNICAL DATA

Colour	As required
Finish	Matt / Semi-glossy to glossy
Flash Point	> 25° C
Volume Solids	36% ±2
Recommended DFT	30-35μ per coat
Theoretical Covering	12.0 M ² /ltr. at 30μ
With 30% Loss	8.4 M ²
Mode of Application	Brush / Roller / Airless /Con. Spray
Airless Spray	Tip size :0.017" – 0.021"
Fluid Pressure	2500 –3000 psi
Drying Time	Touch Dry : 30 mts
Dry to Handle	4 to 6 hours
Hard Dry	8 hours
Overcoating Interval	8 hours minimum, No Maximum
Thinner recommended	Morsun C.R. Thinner
Surface preparation	Blast clean steel surface prime with Morsun Primer for Sunchlor and Intermediate coats as required
Shelf Life	12 months in sealed containers
Packing	20 litres, 4 litres
Limitation	C.R. based paints are not resistant to Oils, Grease & Fats. The film being thermoplastic is liable to soften and decompose above 60°C
Precautions	Ventilate the area to be painted thoroughly to avoid suffocation while application

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.