

MORSUN GLOSSY EPOXY FINISH

PRODUCT CODE

MCS-EF-276

PRODUCT DESCRIPTION

A Polyamide cured glossy Epoxy Finish paint supplied as a two pack system

SUGGESTED USES

As a top coat on sand-blasted surfaces primed with epoxy primer on metal and masonry surfaces, equipment exterior, cylinders, etc. that are exposed a wide range of corrosive conditions

TECHNICAL DATA

Colour	As Required
Finish	Glossy
Flash Point	> 25°C
Mixing Ratio	3 : 1
Pot Life	4 hrs. at 30°C
Volume Solids	55% ±2
Recommended Dft	50 - 75 mic. per coat
Covering Capacity	11.0 M ² /ltr. at 50 mic
With 30 % Loss	7.7 M ² / ltr
Method of Application	Brush/Con./Airless Spray
Airless Spray	Tip Size : 0.018"- 0.024" : Fluid Pressure : 2500- 3500 Psi
Drying Time	Surface Dry : 30 minutes maximum
Hard Dry	12 – 16 hrs
Full Cure	7 days
Overcoating Interval	Minimum 24 hrs. Maximum 7 days (for optimum intercoat adhesion overcoat within 48 hours)
Thinner Recommended	Morsun Epoxy Thinner
Shelf Life	12 months
Surface Preparation	Blast clean to Sa 2 ½ and prime with epoxy primer, ensure surface free from all contaminants
Standard Packing	20 Litres
Limitations	Tends to chalk when continuously exposed to ultra violet rays

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.