

MORSUN EPOXY ALUMINIUM PRIMER

PRODUCT CODE

MCS-EP-229

PRODUCT DESCRIPTION

A two component Polyamide cured Epoxy Aluminium Primer ideal for use on exterior hull of ships from bottom to boot top area and decks. It ensures excellent corrosion resistance of the hull and provides a suitable base for the subsequent topcoats

SUGGESTED USES

As an Anticorrosive primer on blast cleaned steel surfaces of outer hull of ships including bottom, boot-top and main deck area

TECHNICAL DATA

Colour	Bronze
Finish	Semi Glossy with Metallic Lusture
Flash Point	> 25°C
Volume Solids	50% ±2
Recommended DFT	40μ
Covering Capacity	12.5 M ² /ltr. at 40μ
With 30% Loss	8.75 M ² /ltr
Method of Application	Brush/Roller/Con./Airless Spray
Airless Spray	Tip Size : 0.017" – 0.021"
Fluid Pressure	2500 – 3000 psi
Thinner Recommended	Morsun Epoxy Thinner
Drying Time	Surface Dry : 20 – 30 mts
Hard Dry	8 – 10 hrs
Overcoating Interval	Minimum 8 – 10 Hours. Maximum None
Surface Preparation	Blast clean new steel surface to be painted to work the surface may be cleaned by mechanical tooling, chipping, wire brushing, etc. Ensure the surface is free from all contaminants like oil, grease, dust, rust, etc. prior to application of primer
Shelf Life	12 Months
Packing	4 Litres, 20 Litres

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.