

MORSUN EPOXY STOVING PRIMER GREY

PRODUCT CODE**MCS-EP-235****PRODUCT DESCRIPTION**

A specially designed single pack Epoxy Stoving

SUGGESTED USES

Primer for application on metallic substrates. On stoving as per schedule it provides a smooth finish for the subsequent top coat

TECHNICAL DATA

Colour	Grey
Finish	Smooth Egg-Shell
Flash Point	> 25° C
Volume Solids	42% ± 2
Recommended DFT	40 µ
Covering Capacity	10.5 M ² /ltr. at 40 µ
With 30% Loss	7.3 M ²
Method of Application	Airless/Con. Spray
Airless Spray	Tip size: 0.018" - 0.024"
Fluid Pressure	2500 – 3000 psi
Stoving Schedule	130°C for 25 – 35 minutes (Allow flash-off time of 10 – 15 minutes before stoving)
Recommended Thinner	Morsun Epoxy Thinner
Shelf Life	12 Months in sealed containers under room temperature
Surface Preparation	Surface should be thoroughly cleaned, free from all contaminants
Packing	20 Litres, 4 litres

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.