

MORSUN HR ALUMINIUM PAINT 400°C (CONFORMING TO IS-13183)

PRODUCT CODE**MCS-HR-396****PRODUCT DESCRIPTION**

A specially formulated Silicone modified Resin based lustrous Aluminium paint designed for use in areas where heat resistance is required along with resistance to weather. Suitable for use on stacks, ducting, equipment, piping, chimney and other facilities where constant working temperature is around 400°C

TECHNICAL DATA

Temperature	400°C dry heat
Weatherability	Good
Colour	Aluminium
Finish	Lustrous
Flash Point	> 25(C
Volume Solids	30% ± 2
Recommended DFT	20-25 µ per coat
T.C.C	15.0 M ² /ltr. at 20 µ
With 30% Loss	10.5 M ²
Method of Application	Con. Spray / Brush
Recommended Thinner	Morsun Epoxy Stoving Thinner
Drying	Surface Dry : 1 hour
Hard Dry	Overnight
Overcoating Interval	24 hours minimum
Shelf Life	12 Months in sealed containers under room temperature
Surface Preparation	Surface should be thoroughly cleaned, free from all contaminants and suitably primed
Packing	20 Litres, 4 litres

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.