

MORSUN TOP COAT EXTERIOR ENAMEL (CONFIRMING TO IS-6951)

PRODUCT CODE**MCS-NS-701****PRODUCT DESCRIPTION**

A superior quality full gloss Enamel based on Synthetic Resin and weather resistant pigments. The Material is used in painting system for finishing of the weather work areas of ships

SUGGESTED USES

Recommended for use both as a protective and decorative coating for interior and exterior areas above water with good application properties and flow. It dries in a short time providing a smooth finish

TECHNICAL DATA

Colour	As required
Finish	Glossy
Flash Point	> 30° C
Volume Solids	47% ±2
Recommended DFT	50μ
Theoretical Covering	9.4 M ² per ltr. at 50μ
With 30% Loss	6.5 M ² per ltr
Mode of Application	Brush / Roller /Airless/Con. Spray
Airless Spray	Tip size : 0.015"-0.021"
Fluid Pressure	2000-2500 psi
Thinner Recommended	Morsun G. P. Thinner
Drying Time	Surface Dry : 6 hour maximum
Hard Dry	18 hours maximum
Overcoating Interval	18 hours Minimum, No Maximum
Surface Preparation	Surface should be free from all contaminants dry and suitably primed
Shelf Life	12 months
Packing	20 litres, 4 litres
Precautions	Ventilate the area to be painted thoroughly to avoid suffocation while application

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.