

MORSUN VARNISH BLACK JAPAN TO IS : 341

PRODUCT CODE**MCS-NS-702****PRODUCT DESCRIPTION**

This is based on synthetic resin and drying oil, best quality material to meet standard requirement

SUGGESTED USES

This material is used for protection and decorating interior works, usually wooden surface

TECHNICAL DATA

Colour	Black
Finish	Glossy
Volume Solids	40 ±2 %
Recommended Dft	25-35 µ
Theoretical Covering	14.0 M2 at 30µ
Method of Application	Brush / Roller for small area, Conventional/ Airless spray for bigger areas
Heat Resistance	Upto 60°C dry heat (Intermittently)
Thinner Recommended	GP Thinner
Airless Spray	Tip size: 0.015" - 0.019" : Fluid pressure: 2000 - 2500 psi
Drying Time	Surface Dry: 4-7 Hours
Tack Free	8-12 hours
Hard Dry	24 Hours
Flash Point	30 deg C
Overcoating Interval	18 hours Minimum 24 days Maximum
Shelf Life	12 Months in sealed container stored at room temperature
Packing	20 litres, 4 litres
Precautions	Avoid inhalation. Take necessary precautions to avoid contact with skin or eyes. Ventilate the area

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.