

MORSUN SYNTHETIC EXTERIOR ENAMEL (CONFIRMING TO CQAE(M)/SS/98)

PRODUCT CODE**MCS-NS-704****PRODUCT DESCRIPTION**

A superior quality glossy Enamel based on Synthetic Resin and weather resistant pigments Paint conforms to CQAE(M)/SS/98 Specification

SUGGESTED USES

Recommended for use both as a protective and decorative coating for interior and exterior areas above water / ground with good application properties and flow. It has good weathering properties and gloss retention

TECHNICAL DATA

Colour	Assorted
Finish	Smooth and Glossy
Solid Volume	38% $\pm$ 2
Recommended DFT	50 μ
Theoretical Covering	7.6 M ² per ltr. At 50 μ
With 30% Loss	5.32 M ² per ltr
Mode of Application	Brush / Roller /Airless/Con. Spray
Airless Spray	Tip size : 0.015"-0.021"
Fluid Pressure	2000-2500 psi
Thinner Recommended	Morsun G. P. Thinner. Drying Time , Max : Surface Dry : 4 hour
Hard Dry	12 hour
Tack Free	24 Hour
Overcoating Interval	24 hours Minimum, No Maximum
Surface Preparation	Surface should be free from all contaminants dry and suitably primed
Scratch Hardness	After 48 Hr drying passes 1000g test As per IS-101
Flash Point	Not below 30 deg C
Shelf Life	12 months
Packing	20 litres, 4 litres

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.