

MORSUN SUNCHLOR PRIMER GREY CONFORMING TO DEF/STAN/80-72 (PATT NO. N8010-000460)

PRODUCT CODE**MCS-NS-712****PRODUCT DESCRIPTION**

A high build primer based on Chlorinated Rubber with high quality plasticizers and suitable pigments

SUGGESTED USES

Recommended for use on the outer hull, decks, superstructures and interior area of ships as a primer which should be top-coated with Morsun Sunchlor Finish Paint

TECHNICAL DATA

Colour	Red/Grey/Off-white
Finish	Semi-glossy
Flash Point	> 32°C
Volume Solids	42 % ±2
Recommended DFT	40-50μ
Theoretical Covering	8.4 M ² /ltr. at 50μ
Mode of Application	Brush / Roller / Airless / Con. Spray
Airless Spray	Tips size : 0.021"-0.026"
Fluid Pressure	2500-3000 Drying Time , Hard dry : 1 Hour
Overcoating Interval	24 hours Minimum, No Maximum
Thinner Recommended	Morsun C.R. Thinner
Surface Preparation	Degrease and blast clean to Sa 2½ or prepare the surface mechanically / manually to ST2 and ensure, the surface is free from all contaminants prior to application
Shelf Life	12 months
Standard Packing	20 litres, 4 litres
Limitation	C.R. based paints are not resistant to Oils, Grease & Fats. The film being thermoplastic is liable to soften and decompose above 60°C
Precautions	Ventilate the area to be painted thoroughly to avoid suffocation while application

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.