

MORSUN SYNTHETIC ENAMEL GENERAL SERVICE (PAINT CONFIRMING TO JSS 8010-65)

PRODUCT CODE**MCS-NS-715****PRODUCT DESCRIPTION**

A superior quality Air Drying Finish Based on Synthetic Resin and weather resistant pigments suitable for marine environment. Product confirms to JSS-8010-65 Specification

TECHNICAL DATA

SUGGEST USES	Recommended for use both as a protective and decorative coating for General Service with good application properties and flow. It in a short time providing a smooth finish
Colour	Assorted
Finish	Smooth and Semi Glossy Flash Point Min : 35°C
Volume Solids	42% + 2
Recommended DFT	50μ
Theoretical Covering	8.40 M2 per ltr. At 50μ
With 30% Loss	5.88 M2 per ltr
Mode of Application	Brush / Roller / Airless/Con. Spray
Airless Spray	Tip size : 0.015"-0.021"
Fluid Pressure	2000-2500 psi
Thinner Recommended	Morsun G. P. Thinner
Drying Time	Surface Dry : 4 hours maximum
Hard Dry	8 hours maximum Tack Free : 16 hours maximum
Overcoating Interval	24 hours Minimum, No Maximum
Surface Preparation	Surface should be free from all contaminants Dry and suitably primed
Shelf Life	12 months
Packing	20 liters, 4 liters
Precautions	Ventilate the area to be painted thoroughly To avoid suffocation while application

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.