

MORSUN ANTICORROSIVE CHOCOLATE (TO IS-1404)

PRODUCT CODE

MCS-NS-726

PRODUCT DESCRIPTION

An Anti-corrosive Primer based on basic lead sulphate, white lead and other anti-corrosive pigments. This primer provides an effective barrier against water penetration. It also prepares a sound base for the subsequent anti-fouling coating

SUGGESTED USES

As an Anti-corrosive primer for steel hull of ships for the bottom and boot-top area

TECHNICAL DATA

Colour	Chocolate
Finish	Semi-Matt
Flash Point	> 30°C
Volume Solids	62% ±2
Recommended DFT	40μ
Covering Capacity	15.5M ² /ltr. at 40μ
With 30% Loss	10.9 M ²
Mode of Application	Brush/Roller/Con./Airless Spray
Airless Spray	Tip Size : 0.018" - -0.026" : Fluid Pressure : 2500 – 3500 psi
Thinner Recommended	Morsun G. P. Thinner
Drying Time	Surface Dry : 1 hour maximum : Hard Dry : Overnight
Overcoating Interval	Overnight. Maximum None
Surface Preparation	Blast Clean new steel surface to be painted to Sa 2½. For repair work the surface may be cleaned by mechanical tooling, chipping, wire brushing, etc. Ensure the surface is free from all contaminants like oil, grease, dust, rust, etc. prior to application of primer
Shelf Life	12 Months
Packing	4 Litres, 20 Litres

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.