

MORSUN SUNTHANE (PU) FINISH

PRODUCT CODE

MCS-PU-341

PRODUCT DESCRIPTION

A two pack Polyurethane Finish Coating based on Aliphatic Isocyanate Adduct

SUGGESTED USES

An ideal coating to be used as a topcoat over an epoxy base coat or in a total polyurethane painting scheme. The cured film provides hard, flexible, abrasion resistant coating which has excellent weatherability, gloss and colour retention and is resistant to humid, saline and a variety of chemically polluted environment

TECHNICAL DATA

Colour	As required
Finish	Glossy
Volume Solids	44% +2
Mixing Ratio	Base : Adduct 4 : 1
Pot Life	2 to 4 hours depending on ambient temperature
Recommended dft	40-50 μ
Theoretical Covering	11.0 M2 at 40 μ
With 30% loss	7.7 M2 at 40 μ
Method Of Application	Brush / Roller for small area, Conventional/ Airless spray for bigger areas
Heat Resistance	Upto 120°C dry heat (Intermittently)
Thinner Recommended	Sunthane Thinner
Airless Spray	Tip size: 0.015" - 0.019" : Fluid pressure: 2000- 2500 psi
Drying Time	Surface Dry : 1 hour
Hard Dry	8 to 12 hours
Full Cure	7 days
Overcoating Interval	18-24 hours Minimum 5 days Maximum
Shelf Life	9 months in sealed container stored at room temperature
Packing	20 litres, 4 litres
Precautions	Avoid inhalation. Take necessary precautions to avoid contact with skin or eyes. Ventilate the area

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.