

MORSUN SUNTHANE (PU) PRIMER GREY

PRODUCT CODE
MCS-PU-345
PRODUCT DESCRIPTION

A two pack Polyurethane Primer based on Aliphatic Isocynate Adduct

SUGGESTED USES

An ideal primer, to be applied on blast-cleaned substrates that would be top coated with Sunthane Finish Paint PU-341, PU-342 & PU-343. The cured film provides strong rust preventing base coating for the subsequent top coats

TECHNICAL DATA

Colour	Grey
Finish	Smooth & Matt
Volume Solids	45% +2
Mixing Ratio	Base : Adduct 6 : 1
Pot Life	2 to 4 hours depending on ambient temperature
Recommended dft	40-50 μ
Theoretical Covering	11.25 M2 at 40μ
With 30% loss	7.8 M2 at 40μ
Method Of Application	Brush / Roller for small area, Conventional/ Airless spray for bigger areas
Heat Resistance	Upto 120°C dry heat (Intermittently)
Thinner Recommended	Sunthane Thinner
Airless Spray	Tip size: 0.015"- 0.019" : Fluid pressure: 2000- 2500 psi
Drying Time	Surface Dry : < 1 hour
Hard Dry	8 to 12 hours
Full Cure	7 days
Overcoating Interval	18-24 hours Minimum 7 days Maximum
Shelf Life	9 months in sealed container stored at room temperature
Packing	20 litres, 4 litres
Precautions	Avoid inhalation. Take necessary precautions to avoid contact with skin or eyes. Ventilate the area

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.