

MEDIUM DCO ALKYD 50% IN MTO

PRODUCT CODE**MCS-RE-805****PRODUCT DESCRIPTION**

Medium DCO Alkyd 50% in MTO is DCO based oxidizing alkyd resin for air drying application

SUGGESTED USES

Primers for metals, Industrial and architectural paints

TECHNICAL DATA

ADVANTAGES	It is suitable for high gloss finishes with resistance to yellowing. Typical Properties
Clarity	Clear
Type of Oil	DCO
Solid %	50 + 2 Viscosity 40% in MTO @ 300c in FC4 : 60-80 sec
Acid Value on solid	< 12 mgm KOH/gm
Surface dry	Max. 2 hrs
Tack free dry	6 hrs
Hard Dry	24 hrs
Storage	It should be stored indoors in the original, unopened and undamaged containers in a dry place at storage temperatures 350c for up to 12 months. Exposure to direct sunlight to be avoided

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.