

MEDIUM SOYA ALKYD 50% IN MTO

PRODUCT CODE**MCS-RE-806****PRODUCT DESCRIPTION**

Medium Soya Alkyd Resin 50% in MTO is air drying alkyd resin

SUGGESTED USES

This resin is used in general purpose industrial enamels, varnishes and lacquers

TECHNICAL DATA

ADVANTAGES	Non yellowing good drying. Good gloss retention Good colour retention. Excellent hardness and drying. Typical Properties
Clarity	Clear
Type of Oil	Soyabean oil
Solid %	50 + 2 Viscosity 40% in MTO @ 300c in FC4 : 60-80 sec
Acid Value on solid	5-12 mgm KOH/gm
Surface dry	Max 2 hrs
Tack free dry	4-6 hrs
Hard dry	24 hrs
Storage	It should be stored indoors in the original, unopened and undamaged containers in a dry place at storage temperatures 350c for up to 12 months. Exposure to direct sunlight to be avoided

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.