

DCO LONG ALKYD 60% IN MTO

PRODUCT CODE**MCS-RE-809****PRODUCT DESCRIPTION**

DCO Long Alkyd Resin 60% in MTO is prepared on DCO oil

SUGGESTED USES

This resin is used in decorative and protective air-drying enamels and paints

TECHNICAL DATA

ADVANTAGES	High brush ability Good gloss retention Excellent for economical enamel pigmented. Typical Properties
Clarity	Clear
Type of Oil	DCO oil
Solid %	60 + 2 Viscosity 50% in MTO @ 300c in FC4 : 80-100 sec
Acid Value on solid	< 12 mgm KOH/gm
Surface dry	Max. 2 hrs
Tack free dry	4-7 hrs
Hard Dry	24 hrs
Storage	It should be stored indoors in the original, unopened and undamaged containers in a dry place at storage temperatures 350c for up to 12 months. Exposure to direct sunlight to be avoided

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.