

SOYA LONG ALKYD 75% IN 1:1 MTO/XYLENE

PRODUCT CODE**MCS-RE-812****PRODUCT DESCRIPTION**

Soya Long Alkyd Resin 75% in MTO/Xylene is air drying alkyd resin

SUGGESTED USES

This resin is used in white and coloured synthetic enamels

TECHNICAL DATA

SOYA LONG ALKYD 75% in 1	1 MTO/XYLENE
ADVANTAGES	High brush ability Good gloss retention Excellent for glossy enamel paint. Typical Properties
Clarity	Clear
Type of Oil	Soyabean oil
Solid %	75 + 2 Viscosity 50% in MTO @ 300c in FC4 : 25-30 sec
Acid Value on solid	< 15 mgm KOH/gm
Surface dry	Max 2 hrs
Tack free dry	6 hrs
Hard dry	24 hrs
Storage	It should be stored indoors in the original, unopened and undamaged containers in a dry place at storage temperatures 350c for up to 12 months. Exposure to direct sunlight to be avoided

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.