

MORSUN SILKYD TOPCOAT

PRODUCT CODE

MCS-SC-512

PRODUCT DESCRIPTION

A single pack silicon alkyd based semi-glossy U.V. resistant topcoat

SUGGESTED USES

This product known for its excellent gloss and colour retention is ideal for use as a topcoat to any painting system (viz. Alkyd, C.R. or Epoxy) on boot-top, topside, decks, superstructure and other locations on the above water area exposed to weather. When dried the coating provides a film resistant to severe marine conditions

TECHNICAL DATA

Colour	As required
Finish	Semi-glossy
Flash Point	> 30°C
Volume Solids	48% ±2
Recommended DFT	35-40μ per coat (Two coats)
Theoretical Covering	12 M2 at 40μ
With 30% Loss	8.4 M2
Mode of Application	Brush / Roller / Airless /Con. Spray
Airless Spray	Tip size :0.017" – 0.021"
Fluid Pressure	2500 –3000 psi
Thinner recommended	Morsun G.P. Thinner
Drying Time	Surface Dry : 1 hour
Tack Free	2-3 hours
Hard Dry	Overnight
Overcoating Interval	Overnight
Surface preparation	Ensure surface to be coated is free from all contaminants and is suitably primed. Blast clean new steel surfaces to Sa 2½ prime with EP-231 (two coats). Aluminium substrates shall be primed with one coat of EP-231 followed by one coat of Morsun Primer Red/Grey/Yellow
Shelf Life	12 months in sealed containers
Packing	20 litres, 4 litres

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.