

## MORSUN SYNTHETIC VARNISH IS:337

### PRODUCT CODE

**MCS-VR-625**

### PRODUCT DESCRIPTION

This is based on synthetic resin and drying oil, best quality material to meet standard requirement

### SUGGESTED USES

This material is used for protection and decorating interior works, usually wooden surface

### TECHNICAL DATA

|                       |                                                                                                     |
|-----------------------|-----------------------------------------------------------------------------------------------------|
| Colour                | Clear and Transparent                                                                               |
| Finish                | Glossy                                                                                              |
| Volume Solids         | 43 ±2 %                                                                                             |
| Recommended dft       | 20-25 µ                                                                                             |
| Theoretical Covering  | 17.20 M2 at 25µ                                                                                     |
| Method of Application | Brush / Roller for small area, Conventional/ Airless spray for bigger areas                         |
| Heat Resistance       | Upto 60°C dry heat (Intermittently)                                                                 |
| Thinner Recommended   | GP Thinner                                                                                          |
| Airless Spray         | Tip size: 0.015"- 0.019" : Fluid pressure: 2000- 2500 psi                                           |
| Drying Time           | Surface Dry: 3-4 Hours                                                                              |
| Tack free             | 6- 7 hours                                                                                          |
| Hard Dry              | 24 Hours                                                                                            |
| Flash Point           | 30 deg C                                                                                            |
| Overcoating Interval  | 18 hours Minimum 24 days Maximum                                                                    |
| Shelf Life            | 12 months in sealed container stored at room temperature                                            |
| Packing               | 20 litres, 4 litres                                                                                 |
| Precautions           | Avoid inhalation. Take necessary precautions to avoid contact with skin or eyes. Ventilate the area |

Disclaimer: The information provided herein is derived from the best available sources and is given in good faith. As conditions of use are beyond our control, the Company gives no warranty, expressed or implied, and assumes no liability in connection with any use of this information.